

## 腐蚀性流体与泵的浸湿部件匹配参考表

### Corrosive fluid parameter & Wetted parts of pump select

腐蚀性流体 Corrosive fluid	5	10	15	20	25	30	35	40	45	50	55	60	65	70	75	80	85	90	95	100
Acetic Acid(Ambient) 醋酸 ( 常温 )	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	SST	SST	SST
Acetic Acid(Hot) 醋酸 ( 热的 )	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST
Acetic Acid(Boiling) 醋酸 ( 沸腾的 )	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST
Chromic Acids(Conc) 铬酸	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Nitric Acid 硝酸	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST	SST
Phosphoric Acid(Ambient) 磷酸 ( 常温的 )	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Phosphoric Acid(Hot) 磷酸 ( 热的 )	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Phosphoric Acid(Boiling) 磷酸 ( 沸腾的 )	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Potassium Hydroxide(<60°C/140 ℉) 氢氧化钾 ( < 60°C)	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Potassium Hydroxide(<60°C/185 ℉) 氢氧化钾 ( < 60°C)	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	SST
Sodium Hypochloride 氯化钠	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Magnesium Hydroxide 氢氧化镁	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Muriatic Acid 盐酸	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Sodium Hydroxide 氢氧化钠	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Hydrochloric Acid 盐酸	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Hydrochloric Acid(Boiling) 盐酸 ( 沸腾的 )	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Hydrofluoric Acid(Ambient) 氢氟酸 ( 常温的 )	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Hydrofluoric Acid(Boiling) 氢氟酸 ( 沸腾的 )	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Hydrofluoric Acid(Conc) 氢氟酸	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Sulfuric Acid(<51.6°C/125 ℉) 硫酸 ( < 51.6°C)	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP	PP
Sulfuric Acid(51.6~79.4°C/125~175 ℉) 硫酸 ( > 51.6°C ( < 79.4°C)	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF
Sulfuric Acid(Boiling) 硫酸 ( 沸腾的 )	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF	PVDF

**PP**  
聚丙烯

**SST**  
不锈钢

**PVDF**  
聚偏氟乙烯